


CLAIMS

1. A modified diene- α -olefin copolymer which is represented by the formula (1) below and has $\text{H}_2\text{C}=\text{C}(\text{R}^5)-\text{COO}-$ in
5 at least a part of the ends,



wherein R^1 and R^2 independently represent a hydroxyl group or
10 $\text{H}_2\text{C}=\text{C}(\text{R}^5)-\text{COO}-$, R^3 s, R^5 s, and R^6 s independently represent a hydrogen atom or an alkyl group having 1 to 10 carbon atoms, R^4 s independently represent a phenyl group, a pyridyl group, a chlorine atom, a cyclohexyl group, or a carbonyloxyalkyl group, and 1, m, and n represent the number of repetition.

15

2. The modified diene- α -olefin copolymer according to claim 1, having a number average molecular weight of 300 to 10,000.


20

3. The modified diene- α -olefin copolymer according to claim 1, wherein the amount of α -olefin compounds is 1 to 90 mol% in the total amount of the copolymer.


4. The modified diene- α -olefin copolymer according to claim 1, wherein the proportion of the end with a structure of $\text{H}_2\text{C}=\text{C}(\text{R}^5)-\text{COO}-$ is 20 to 100 mol% of the total end groups.

5 5. The modified diene- α -olefin copolymer according to claim 1, wherein the R^4 is a phenyl group.

6. A method for producing the modified diene- α -olefin copolymer according to claim 1, comprising reacting a
10 diene- α -olefin copolymer shown by the following formula (2) with an unsaturated carboxylic acid shown by the following formula (3) or a derivative thereof, adding 1 mg to 1 g of a radical scavenger per 100 g of the copolymer,



15 wherein R^3 s and R^6 s independently represent a hydrogen atom or an alkyl group having 1 to 10 carbon atoms, R^4 s independently represent a phenyl group, a pyridyl group, a chlorine atom, a
20 cyclohexyl group, or a carbonyloxyalkyl group, and 1, m, and n represent the number of repetition,



wherein R⁵ is a hydrogen atom or an alkyl group with 1 to 10 carbon atoms.

- 5 7. The method for producing the modified diene- α -olefin copolymer according to claim 6, wherein the diene- α -olefin copolymer is reacted with the unsaturated carboxylic acid or a derivative thereof in a solvent, the concentration of the copolymer in the solvent being 50 wt% or less.